

Product Technical Data / Product Type: 2827

Eabric Type

гаристуре	
Needlefelt, Thermal Bonded, Laminated Nonwoven	
Composition	
Polyester	
Polypropylene	
SAF™	
Polyester / Polypropylene Laminate, Top	
Polyethylene Laminate, Bottom	

Physical Characteristics	
Total Weight (g/m ²)	250
Thickness (mm)	2.0

Absorbency (0.9% Saline)	
Absorbent capacity (g/g)	11
Absorbent volume (g/m ²)	>2,700

Absorbency (DM Water)	
Absorbent capacity (g/g)	15
Absorbent volume (g/m ²)	>3,750

All tests are carried out in accordance with standard protocols. This document does not constitute a specification for the above material, it is provided as an indication only.

Technical Absorbents Ltd. 1 Moody Lane, Great Coates, Grimsby, North East Lincolnshire, DN31 2SS. United Kingdom

exploreSAF.com

a Technical Absorbents product